

Synthesis and characterization of Phytofabricated Zinc Oxide Nanoparticles with Pharmacological and Environmental Applications

Saifullah Khan

Department of Biotechnology, Genetics, Forensic, and Microbiology, University of Swat, 19130, Pakistan

Mohsin Ali

Department of Botany, Mirpur University of Science and Technology, AJK Bhimber Campus

Kainat Qureshi

Department of Food Quality & Safety Research Institute Organization: Pakistan Agricultural Research Council

Shah Naeem

Department of Biotechnology, Genetics, Forensic and Microbiology, University of Swat, Khyber Pakhtunkhwa, Pakistan

Fatima Hayat

Institute of Biotechnology and Genetic Engineering, The Agriculture University, Peshawar, Pakistan

M Hisham Al Nasir

Department of Physics, Riphah International University, Islamabad 44000, Pakistan

Saher Naveed

Centre of Agricultural Biochemistry and Biotechnology, University of Agriculture, Faisalabad, 38000 Pakistan

Saima Sher Afghan

Department of Microbiology, University of Haripur, Khyber Pakhtunkhwa, Pakistan

Muhammad Imran

Department of Botany, PMAS Arid Agriculture University, Rawalpindi, Pakistan

Rida Nisar*

Department of Horticulture, Faculty of Agriculture, Gomal University, Dera Ismail Khan, Khyber Pakhtunkhwa 29220, Pakistan Email: ridanisar001@gmail.com

Author Details

Keywords: ZnO Nanoparticles, Green Synthesis, *Acacia Nilotica*, Biological Applications, Environmental Application.

Received on 20 Feb 2026

Accepted on 17 Mar 2026

Published on 27 Mar 2026

Corresponding E-mail & Author*:

Rida Nisar*

Department of Horticulture,
Faculty of Agriculture, Gomal
University, Dera Ismail Khan,
Khyber Pakhtunkhwa 29220,
Pakistan Email:
ridanisar001@gmail.com

Abstract

A significant challenge has recently emerged in the field of nanotechnology and nanoscience, prompting the development of greener synthesis approaches. Among these, the production of metal oxide nanoparticles using plant extracts has gained considerable attention due to its advantages over conventional chemical and physicochemical methods. In the present study, *A. nilotica*-mediated zinc oxide (ZnO) nanoparticles were synthesized through an eco-friendly and cost-effective green synthesis approach. The synthesized nanoparticles were comprehensively characterized using several spectroscopic and microscopic techniques, including UV–Visible spectroscopy (UV–Vis), Dynamic Light Scattering (DLS), Fourier Transform Infrared Spectroscopy (FTIR), X-ray Diffraction (XRD), Scanning Electron Microscopy (SEM), and Energy Dispersive X-ray (EDX) analysis. XRD and DLS results confirmed the hexagonal nanocrystalline

structure of the ZnO nanoparticles. FTIR analysis indicated the presence of multiple functional groups associated with phytochemicals involved in nanoparticle stabilization. UV–Vis spectroscopy confirmed the optical properties of the ZnO nanoparticles. The synthesized nanoparticles exhibited an average size of 68.3 nm with a band gap energy of 2.71 eV. SEM images revealed that the ZnO nanoparticles possessed a clover-leaf morphology, while EDX spectra verified the elemental composition, confirming the presence of zinc and oxygen. The biosynthesized nanoparticles demonstrated promising biomedical activities. The highest antileishmanial activity recorded was 68%, anti-inflammatory activity reached 78%, total antioxidant capacity (TAC) was 79.1%, antibacterial activity showed a zone of inhibition (ZOI) of 22.1 mm, and a maximum growth inhibition of $85 \pm 2.1\%$ was observed against *A. rabiei*. In addition to biomedical applications, the environmental potential of the nanoparticles was evaluated for cadmium removal, achieving an adsorption efficiency of 85.3% within 120 minutes. Overall, the bio-inspired ZnO nanoparticles exhibited significant biomedical and environmental potential. These findings suggest that such green-synthesized nanoparticles warrant further investigation to enhance their applicability and scalability for practical applications.

Introduction

Nanotechnology is a vibrant and quick-growing field having acquaintance from multiple fields like natural sciences, biological sciences and other sciences. The term “nano” refers to very small (1–100 nm). The inimitable characteristics of nanoparticles (NPs), including smaller size larger surface area, variation in structural properties, and many other physicochemical properties make them better candidates to use in fields of medicine, environment, and agriculture (Bhilkar et al. 2023). Due to their diverse nature, nanoparticles are categorized as nanotubes, nanocrystals, nanoflower, nanowires, etc (Perwez et al. 2023). The most common nanoparticles and metal oxide nanoparticles are silver (Ravindran et al. 2013), zinc oxide (Khalafi et al.2019), titanium oxide (Chanani et al. 2023) nickel oxide (Buazar et al. 2023), and calcium oxide (Rahimi et al., 2023), and iron oxide (Safari et al. 2020). These are most stable under extreme conditions such as high temperature and pressures and some of them are considered nontoxic and even contain mineral elements essential to human health. Hence, bio-nanocomposites have been noted as a promising alternative in food packaging market.

Different biological routes have been used for the synthesis of nanoparticles previously. The organic procedure of preparation comprises the use of bacteria (Pantidos et al. 2014), fungi (Siddiqi et al. 2016), algae (Moavi et al. 2021) and plants (Wang et al. 2023). The preparation of bio-inspired NPs has gotten huge attention in recent times in a progressive way because of the great benefits in terms of eco-friendly and cost-effective nature. The NPs prepared using plants sources are have good stability and the synthesis rate is faster as compared to that of microorganisms (Khalafi et al. 2019). It is worth mention that the plant-assisted bioreduction strategy for NiO NPs fabrication has received glob attention as a renewable and sustainable supplier (Buazar et al. 2016, Koopi et al. 2018, Buazar et al. 2023).

Among different types of nanoparticles, metal-source NPs are advantageous due to their non-toxic behavior to the biotic and a-biotic factors of the environment (Liaqat et al. 2024). The phyto based synthesis of ZnO nanoparticles is very useful as the biological molecules existing in the leaves extract work as effectual capping mediators thus showing a critical character in NPs preparation. The capping elements seem to stabilize the nanoparticles through multiple traditions such as steric, electrostatic stabilization, and hydration interaction. The stabilization of NPs directly related to the functions of nanoparticles in different biological assays (Pantidos et al. 2014). Metal oxide nanoparticles (MO NPs) also have a vital part in multiple fields especially in nanomedicine, environment, and farming (Campaña et al. 2023, Alavi at al. 2021).

Amongst various NPs, zinc oxide NPs are excessively used for their harmless behavior and possess excellent physio-chemical and biological characteristics (Elmaghraby et al. 2024). ZnO NPs have multiple exciting properties including electric conductivity, optical transparency, piezoelectricity, wide availability, non-toxicity, stability, and cost effectivity (Sabouri et al. 2022, Zafar et al. 2024). They have applications in multiple fields, such as catalysis, solar batteries, varnishes, plastics, paints, pharmaceutical items, and optoelectronic apparatuses (Tortella et al. 2023). It commonly works as a protective agent in sunscreen products and cosmetics to the efficiency of filtering ultraviolet irradiations (Guerrini et al. 2018). ZnO NPs are also better considered for their antifungal and antibacterial activity (Ali et al. 2018). ZnO NPs can interact with phospholipids bi-layer in the cell membrane and alter the structural configuration of the cell membrane, which causes to forfeiture of membrane function, veracity, and lastly to microbial death (Nadhiya et al. 2023, Neolaka et al. 2022). Now-a-days, zinc oxide nanoparticles are also employed as exterior antimicrobial agents for microbial growth inhibition in, textile items, mouth sprays, lotion ointments, and food packages (Eleryan et al. 2023).

Globally, environmental destruction issues are presently instigating pollution and impairing natural resources owing to the massive upsurge in the human population and the evolution of industrial activities (Raha et al. 2022). Heavy metals are the natural component of the Soil. The amount of HMs in soil, and different water sources is surpassing the tolerable range leading to a veiled threat to the biotic community (Verma et al. 2021). Among HMs Cadmium (Cd) is considered a very lethal environmental contaminant because they harmful to plants, animals, and humans. Different conventional processes are used to get rid of HMs from polluted water bodies (Theerthagiri et al. 2019, Pillai et al. 2020, Li et al. 2023). However, these traditional procedures have certain limitations such as its cots-intensive, requiring large amounts of energy and released secondary pollutants (Murali et al. 2023, El-Nemr et al. 2022). Hence, environment friendly and low-cost organic materials are required for the amputation of HMs. Currently, nano-bioremediation has been established as an auspicious technique for declining HMs pollution in the ecosystem and advanced nanoparticles have increased substantial interest. ZnO NPs have been used frequently to eliminate heavy metals from contaminated water for their small size, and biocompatible nature (Bujang et al. 2020, Nelson et al. 2018).

Medicinal plants are playing a key part in the treatment of several disorders (Onyancha et al. 2022). Plants are rich in phyto-active compounds; hence they are used in the production of multiple types of medicines across the globe for the management of multiple health problems (Neolaka et al. 2023). *Acacia nilotica* is commonly applied for, fuel, medicine and wood production in Pakistan (Eldeeb et al. 2024). Previous studies proved that *A. nilotica* has pharmacological abilities to treat skeleto-muscular and stomach problems (Bairagi et al. 2023, Dhiman et al. 2021, Ozkan et al. 2016,). Leaves extract have shown analgesic, anti-platelet, anti-hyperglycemic activity, and antioxidant potential (Koparde et al. 2017, Hashim et al. 2022, Khanum et al. 2022, Ghauri et al. 2023). The hepatoprotective properties of the *Acacia nilotoica* bark extracts and anti-microbial potential also investigated (Saleem et al. 2018, Arbab, et al. 2015, Bukhari et al. 2010).

To the best of our knowledge, this is the first study to prepare ZnO nanoparticles from the active phytochemical constituents of the *A. nilotica* extract. Additionally, our study explores the unique optical and catalytic properties of these nanoparticles, revealing novel applications in both biomedical and environmental remediation. Furthermore, we investigate the interactions between nanoparticles and biological systems at the molecular level, shedding new light on their potential toxicity and therapeutic efficacy. The scope of our work spans multiple disciplines, including materials science, chemistry, biology, and environmental science. We systematically characterize the physicochemical properties of the synthesized nanoparticles using advanced spectroscopic and microscopy techniques. Moreover, we assess their performance in various applications such as drug delivery, and pollutant removal. These advancements have the potential to revolutionize fields such as healthcare, environmental monitoring, and energy production. Overall, our work not only expands the frontiers of scientific understanding but also holds promise for addressing pressing societal challenges through innovative nanoparticle solutions.

Materials and methods

Chemicals

Zinc Nitrate Hexahydrate {Zn (NO₃)₂·6H₂O}, sodium hydroxide (NaOH), Dimethylsulfoxide (DMSO), DPPH (2, 2-diphenyl-1-picryl hydrazyl), methanol (CH₃OH), Whatman filter paper no.1, amphotericin-B, ascorbic acid, bovine serum albumin (BSA), Tris buffer, Diclofenac sodium. All the chemicals were taken from Sigma Aldrich utilized without further purification. The glass apparatus used for experiment were appropriately splashed, and autoclaved.

Collection and processing of plant samples

A. nilotica was collected from the Bannu, Khyber Pakhtunkhwa (KP), Pakistan. The wild-collected *A. nilotica* plant was collected following standard guidelines. The collected plant was identified botanist submitted to the herbarium with a voucher specimen (Ak-2226).

Plant extract preparation

For the synthesis of the extract, leaves of *A. nilotica* were collected and splashed thoroughly in running tap water to eradicate dust and other debris attached to the leaves surface. Then all the cleaned leaves were shade dried and converted to powder form via a grinder. The prepared powder was blended in a 250 ml of double distilled water (DDW), boiled for 15 min, and then incubated for 15 min in a water bath at 80° C. The obtained mixture was cooled down and filtered through muslin fabric followed by filtered via Whatman filter paper no. 1 and placed at 4° C for one week.

Qualitative analysis on phytochemical constituents of plant extracts

Qualitative phytochemical analysis encompasses the process of identifying and detecting various constituents within plant samples. Its objective is to determine the existence or non-existence of specific phytochemicals or classes of compounds, including alkaloids, flavonoids, terpenoids, phenolic compounds, proteins, saponins, glycosides, steroids, anthocyanins, oils, quinones, and tannins. The Mayer's test was for alkaloids, Benedict's test for glycosides, Millon's test for protein, Alkaline reagent test for flavonoids, Salkowski's test for steroids, terpenoids, Copper acetate test for phenolic compounds were used for the identification of biomolecules. The Qualitative phytochemical analysis was performed through the previously published protocol (Ullah et al, 2018, Abid et al. 2020).

Preparation of ZnO NPs

For this purpose, 1 mM solution of Zinc Nitrate Hexahydrate $\{Zn(NO_3)_2 \cdot 6H_2O\}$ was synthesized. Plant extract prepared in distilled water and Zinc Nitrate Hexahydrate $\{Zn(NO_3)_2 \cdot 6H_2O\}$ solution was blended in a ratio of 1:2. The obtained mixture was heat up and continuously stirred using hot plate for 90 mins at 80° C. The change in color confirmed the process of reduction. The then obtained mixture was centrifuged for 35 min at 6,000 rpm and laved with DDW (Sharmila et al. 2019). To attained desiccated powder, the pallet was located in an incubator for 4 hr at 100° C. Dried matter was calcinated for 2 hr at 600° C to get crystalline ZnO NPs. These synthesized nanoparticles were characterized through various techniques prior to their application in various biological techniques.

Characterization of ZnO NPs

UV-Vis Spectroscopy

The optical properties of the bio-inspired ZnO NPs in a colloidal suspension was assessed through ultraviolet-visible spectroscopy. The bandgap energies of the nanocomposites were calculated from diffuse reflectance UV-Vis. The bandgap of synthesized nanocomposite was calculated by the following equation 1:

$$(\alpha h\nu)^2 = K(h\nu - E_g) \quad (1)$$

Where α shows absorption coefficient, $h\nu$ represents photon energy (eV), K indicates absorption index and E_g is bandgap energy.

XRD analysis

X-ray diffractometer was applied for the confirmation of the crystalline behavior of bio-fabricated NPs. The results of the XRD were explained based of their atomic structure, angles and planes where the diffraction takes place in solid sample samples. The Scherrer's formula was used to calculate the nanoparticles' sizes as follows:

$$D = 0.9\lambda / \beta \cos \theta \quad (2)$$

Where D shows average crystalline size, K denotes shape factor, λ represent X-Ray wavelength, β shows full width half maximum and θ shows diffraction angle.

FTIR spectroscopy

FTIR spectroscopy of ZnO NPs was achieved for the purpose to explore structural properties and confirmation of different functional groups. For FTIR the NPs sample was synthesized using to the previous standard procedure (Kamal et al. 2022) and then measured in FTIR spectroscope (Housseiny et al. 2020).

SEM and EDX analysis

SEM was performed to study the topographical characteristics of the synthesized NPs. SEM was achieved following the standard protocol [51]. The EDX spectroscopy was done to explore the elemental alignment, their purity percentage and confirmation of

the existence of oxygen and zinc. EDS was performed to analyze the qualitative analysis of the elements in NPs in scattered pattern. The EDS was performed following the former published protocol.

DLS analysis

DLS was executed to determine the polydispersity index (PDI), zeta potential (ZP), and hydrodynamic size distribution. DLS analysis was performed using the previous protocol (Fadwa et al. 2021).

Biological Applications of the ZnO NPs

Antileishmanial assay

To assess the antiparasitic efficacy of the bioinspired ZnO nanoparticles they were applied against *Leishmania tropica* promastigotes, using former standard protocol. Each assay tubes contain 5 mL of medium with 1×10^5 parasites/mL of *L. tropica* promastigotes. Then, 5 mL of every dose (20, 40, 80, and 160 $\mu\text{g/ml}$) of the prepared nanoparticles was transferred to each tube and incubated at 28 °C. During this activity, amphotericin-B and DMSO were used as a positive and negative control correspondingly. Parasites count was measured using hemocytometer in all treatments (NPs and control samples) at various times breaks from 24 to 96 h and the percentage (%) inhibition was calculated via the subsequent formula (3):

$$(\%) \text{ Inhibition} = 100 \times \text{Absample}/\text{Abcontrol} \quad (3)$$

In this, Absample shows the absorbance of the ZnO treated sample and Abcontrol mentions to the control sample.

Anti-inflammatory activity

Anti-inflammatory assay of plant extract and ZnO NPs were executed following the aforementioned procedure (Muhammad et al. 2019). Reaction cocktail bovine serum albumin (BSA) was synthesized in saline Tris buffer (PH 6.8). BSA (900 μl) was added with 100 μl of different doses of ZnO (50, 100, 200, 400 and 800 $\mu\text{g/ml}$). Diclofenac sodium ($\mu\text{g/ml}$) was applied as a standard. The reaction was performed following previous protocol and final absorbance was measured at 580 nm (Arora et al. 2014). The activity was executed thrice, and protein denaturation was calculated through the following equation (4):

$$\text{Protein inhibition} = 100 \times (\text{Abs. (control)} - \text{Abs. (sample)}) / \text{Abs. (control)} \quad (4)$$

Antioxidant activities

Various antioxidant activities including total antioxidant capacity (TAC), total reducing power (TRP), and DPPH-free radical scavenging (FRSA) were performed to analyze the antioxidant potential of ZnO NPs at different doses from 50–200 mg/mL (El-Belely et al. 2021).

TAC Determination

To determine TAC, 100 μL of each concentration of ZnO NPs was added separately with reagent using previous published protocol (Kaushik et al. 2019). AA and DMSO was used as a positive and negative control.

TRP determination

For this purpose, we used the potassium-ferricyanide method [56]. DMSO and AA was applied as a negative and positive control. Absorbance of each treatment was measured 580 nm.

FRSA determination

The FRSA was determined using the previously standard protocol (Kaushik et al.2019). % inhibition was calculated through subsequent formula (5):

$$(\%) \text{ FRSA} = 100 \times \text{Ab NPs sample}/\text{Abs Control} \quad (5)$$

Evaluation of the Antimicrobial Activities

Antifungal Activity

To estimate the antifungal efficacy, the prepared ZnO NPs was applied against *Ascochyta rabiei* was performed following the previous standard protocol with a little modification (Emami-Karvani et al. 2011). The preserved *A. rabiei* was freshed on potato dextrose agar (PDA) media prior to the activity for 7 days at 25 ± 1 °C. PDA media was treated with different ZnO NPs doses (0.5, 0.75, and 1 mg/mL). The 4 mm disc of *A. rabiei* was located in the middle of ZnO NPs treated PDA Petri plates. PDA lacking NPS used as a positive control. The treated plates were placed in incubator for one week at 25 ± 1 , and the antifungal potential was calculated using the following formula:

$$\text{Growth Inhibition \%} = 100 \times (C-T)/C \quad (6)$$

Where C refers to the fungus growth in the control plate, and T denotes to the fungus growth in a nanoparticle amended plate.

Antibacterial activity

The Antibacterial potential was determined against *E. coli* through agar well diffusion method (Emami-Karvani et al. 2011). The antibacterial activity was performed at different concentration (5, 10 and 20 mg/mL) according to the previous standard protocol (Emami-Karvani et al. 2011). A positive control using an antibiotic was employed, and a negative control using less than 1% Dimethylsulfoxide (DMSO). After that, plates were kept in an incubator for 24 hours at 30°C. After that, the we measured the inhibition zone in millimeters (mm).

Environmental application

ZnO NPs against metals adsorption

Adsorption activity was executed consuming ZnO NPs against Cd metal. ZnO NPs (1g) was liquified in 100 ml of water having Cd (dosage of 100 mg/L) in flask (250 ml). In this study, the role of various factors like initial concentration of Cd (20-120 mg/l) and time duration (5-120 minutes) on the Cd adsorption were investigated. The prepared mixture of Cd and ZnO NPs was stirred at 120 rpm with the help of a shaker for a fixed time at 25° C. The prepared mixture was filtered and Initial and final Cd concentration were measured in the filtrate through Atomic Adsorption Spectrometer. The adsorption capacity (mg/g) and the adsorption efficiency (%) of the ZnO NPs were calculated following the formula 7 and 8.

$$q_e = \frac{(C_i - C_e)}{W} \times V \quad (7)$$

$$P = \frac{(C_i - C_e)}{C_i} \times 100 \quad (8)$$

C_e refer to the equilibrium Cd concentration, C_i represent the initial concentration of Cd, W denotes the ZnO NPs weight and V denotes volume of the mixture.

Statistical Analysis

All the samples were taken in triplicates and SPSS, version 16.0 <https://www.ibm.com/spss> and OriginPro9 were used to assess it statistically.

Results and Discussion

Qualitative analysis of phytochemical

Qualitative assessment of extracts was accepted by analyzing phytochemical compounds that were present in different parts of plants Table 1. The qualitative analysis of distilled water extracts of *A. nilotica* was carried out to detect the secondary metabolites like alkaloids, quinones, terpenoids, flavonoids, phenolic compounds, glycosides, saponins, steroids, anthocyanins, fats and oils, and tannins. These results are depicted in Table 1. There is a small variation in Qualitative phytochemical constituents were identified by previous researcher worked on *A. nilotica* (Niaz et al. 2023, Buazar et al. 202), which may be due to the nature of the extract and plant physiological responses to their environment.

Sr. No	Secondary Metabolites	AMWD
1	Phenols	+ ++
2	Flavonoids	++
3	Alkaloids	++
4	Terpenoids	+
5	Saponins	-
6	Tannins	-
7	Steroids	++
	Glycosides	+ +
9	Quinones	+
10	Anthocynins	++
11	Fats and oils	+
12	Protein	++

Characterization of NPs

UV-Visible Spectroscopy

The effective production of nanoparticles was revealed thru surface plasmon resonance measurements at a wavelength of 225nm in plant extract (Figure 1a) and 350 nm in ZnO NPs (Figure 1). The cell-free culture's color shifted from golden to creamy which gives the first indications of nanoparticles synthesis which might be due to the secondary metabolites in the cell-free filtrate reduced zinc acetate to produce ZnO NPs (Torfi-Zadegan et al. 2023). The prepared composite showed band gap values of nearly 2.71 eV calculated from the VU data. It has previously been shown that zinc oxide absorbs at a comparable peak at 340 nm (Chikkanna et al. 2019). A little difference in the peak may be due to the precursor material.




Figure 1. UV-Vis spectroscopy of the prepared nanoparticles

XRD Spectroscopy

The XRD configuration of bio-fabricated ZnO nanoparticles displayed seven visible peaks from 10° to 70° . The peak at 32.5° , 34.1° , 37.5° , 48.1° , 56.3° , 63.5° , and 67.2° , respectively (Figure 2). The different peaks indicate different planes 100, 002, 101, 102, 110, 103, 200, and 201. This illustration was indexed crystallographic properties of hexagonal structure of zinc oxide NPs, ensuing and all these peaks were according with the JCPDS no. (036–1451). By means of Debye–Scherer’s equation, the average size of the particle was obtained as 68.3 nm. Similar results were reported by Elumalai et al. (2015). The strongest peak of ZnO NPs, formed in *A. nilotica* extract, confirmed of their highly crystalline nature. The XRD study for zinc oxide nanoparticles is parallel with earlier studies (Jiang et al. 2009). It was previously investigated that the crystalline nature of the NPs plays a pivotal role in their efficacy (Dubey et al., 2013). It has been also observed in earlier studies that Crystalline NPs exhibit excellent antifungal activity via the demolition of the hyphal wall (Oliveira et al., 2019).




Figure 2. XRD of the prepared nanoparticles

FTIR analysis

FTIR spectroscopy of bio-fabricated ZnO NPs is presented in Figure 3. FTIR study was assessed for the purpose to distinguish the different functional groups which participated in the development and capping of ZnO. FTIR analysis depicted seven peaks extending from 500-3500 cm^{-1} . Peaks observed at 628.31 cm^{-1} and 833.52 cm^{-1} verified durable stretching of C-Br and medium bending of C=C, individually. The peak 1222.51 cm^{-1} refers to medium C-N stretching of amine found in the *A. nilotica* extract, gives confirmation of protein in a prepared ZnO NPs, comes from the reduction process. The peaks perceived at 1417.1 cm^{-1} and 1609.9 cm^{-1} refers to medium O-H bending and strong

C=O stretching correspondingly. A peak found at 2167.65 cm^{-1} denotes strong N=C=N stretching. A prominent peak detected at 3255.1 cm^{-1} indicated the occurrence of strong and broad O-H stretching of carboxylic acid. Almost similar results were reported by several scientist worked on bio-fabricated NPs (Singh et al. 2020, Sumaira et al. 2018).




Figure 1. FTIR Analysis of the prepared nanoparticles

SEM and EDX analysis

SEM was performed to examine the texture and distribution of the ZnO NPs. The morphological characteristics of was examined via SEM analysis (Figure 4a). SEM micrograph depicted that ZnO NPs are present in white cottony appearance in clover leaf shape distributed homogeneously. A uniform distribution of NPs provides us better information on a morphological analysis and estimated nanoparticles size (Sumaira et al. 2018). All these results of SEM are algin to the previous work (Abbasi et al. 2017). The elemental composition and configuration of the prepared nanoparticles was assessed by EDX spectrum. The EDX analysis of ZnO nanoparticles confirmed the presence of zinc (Zn) and oxygen (O), which confirmed the confirmation of ZnO-NPs, along with some other elements including carbon (20.8%) and sodium (6.9%), which may come from the plant extract (Figure 4b). The high percentage of carbon may be due to organic based (plant extract) synthesis of the nanoparticles. The weight percentage of Zn and O examined are 51.4, and 20.8% separately. All these findings are consistent with the former study conducted by the nanotechnologists (Agarwal et al. 2020). Through EDS element distribution was also investigated. The image (Figure 5) displays that nanoparticles are well disseminated on the carbon foil. Figure 5 could

deliver the element distribution after two minutes. These results demonstrate the capability of the EDS detector for quick identification of the ZnO nanoparticles.




Figure 4. SEM (a) and EDX (b) of the prepared nanoparticles





Figure 5. SDS Analysis of the prepared nanoparticles

Zeta potential (ZP)

ZP, the study was applied for the confirmation of charge on the periphery of ZnO NPs, which indicates the electrical nature of ZnO nanoparticles. . The electrostatic repulsion potential between neighbor particles in a suspension is revealed via the ZP value. Nanoparticle suspension with a Zeta potential value of +8.50 to -8.50 mV indicates the high stability of nanoparticles (Sarkar et al. 2014). The ZP analysis confirmed that the surface electrical charge of ZnO NPs was -8.95 mV (Figure 6a). Figure 6b displays the intensity of light scattering and size. The zeta average size of ZnO NPs was 663.5 d-nm with a PDI of 0.523. In green algae and plant-based NPs, ZP was examined to be negative (-) (Janaki et al. 2015). This negative value is owing to the secondary metabolite's attachment to the NPs surface (UI-Haq et al. 2012). In this study, the negative ZP of plant-mediated ZnO NPs might attributable to the chemical constituents and reducing agents along with the NPs size.




Figure 6. Surface electrical charge (a), and intensity of light (b) of the ZnONPs
Antileishmanial Activity

To analyze the antileishmanial activity, the prepared NPs were tested as an antileishmanial agent in various concentrations for a time duration of 96 hr as and their efficiency were described in Figure 7. To assess the antileishmanial potential, promastigotes numbers were counted in in NPs amended and control groups at diverse time duration including 24 h, 48 h, 72h, and 96 h. The antileishmanial potential was enhanced with the enhancing in the amount of ZnO nanoparticles. The antileishmanial potential was examined to be 20%, 30%, 32% and 37% at 20, 40, 80, and 160 $\mu\text{g/ml}$, of 24 h of incubation. Afterward 48 hr of incubation, the ZnO NPs showed antileishmanial efficacy of 27%, 32%, 39%, and 48% at at 20, 40, 80, and 160 $\mu\text{g/ml}$, correspondingly. Afterward 72 hr of incubation, the cells number was further declined in the ZnO amended samples which was 35% at 20 $\mu\text{g/ml}$, 48% at 40 $\mu\text{g/ml}$, 60 % at 80 $\mu\text{g/ml}$ and 68% at 160 $\mu\text{g/ml}$. Later on, a little reduction in antileishmanial potential was observed. This decrease in the potential may be owing to the enervation of ROS from the ZnO nanoparticles. Additionally, MO-NPs have the potential of produce reactive ions, which causing pores in the pathogen wall and affects structural features of the membrane, and leakage of intracellular material and finally leads to pathogen destroying. The substantial findings of our study confirmed that ZnO might be an auspicious tool for leishmaniasis treatment which is in consistence with to earlier studies (Janaki et al. 2015).




Figure 7. Antileishmanial Activity of the Prepared Nanoparticles

Anti-Inflammatory potential

The synthesized ZnO NPs and the plant extract of *A. nilotica* expressed parallel anti-inflammatory efficacy in comparison to standard chemical analgesic (Diclofenac sodium). The plant mediated NPs behaved as an efficient anti-inflammatory agent (Figure 8). The ZnO NPs and *A. nilotica* extract both help to reduce *in vitro* inflammation. The maximum anti-Inflammatory potential of ZnO was determined 45% at 50 $\mu\text{g/mL}$ concentration, 58% at 100 $\mu\text{g/mL}$, 65% at 200 $\mu\text{g/mL}$, 70% at concentration of 400 $\mu\text{g/mL}$, and 78% at 800 $\mu\text{g/mL}$. Further increase in concentration i.e above 800 $\mu\text{g/mL}$ does not show more than 78% inhibition. Comparative study exposed that the ZnO NPs is a better anti-inflammatory agent as compared to plant extract. Previous studies also that plant-based NPs has better anti-inflammatory activity

as compared physically and chemically synthesized NPs and plant extract inflammatory medicine (Abdulazeem et al. 2023).




Figure 8. Anti-Inflammatory potential of the Prepared Nanoparticles

Antioxidant assay

Antioxidant potential of ZnO nanoparticles were assessed at various doses (50–00 µg/ml). Antioxidant potential including TAC, TRP, and DPPH free radical scavenging are depicted in Figure 9. The maximum result for TAC in terms of AA per mg equivalents was measured to be 79.1% for ZnO NPs at 200 µg/mL. TAC confirmed the scavenging power of the ZnO NPs to ROS. TRP was performed to study further about the presence of antioxidant species related to ZnO NPs. This activity was designed to assess the reductones that play vital role in the antioxidant activities (Siripireddy et al. 2017). The highest TRP (65.2%) was attained at 200 µg/mL. The maximum DPPH radical scavenging capacity was 68.7% for ZnO NPs at 2000 µg/mL. These findings are parallel to the previous reported work on bioinspired ZnO NPs (Bhosale et al. 202, Arif et al. 2023).




Figure 9. Antioxidant activity of the prepared nanoparticles

In vitro antibacterial assay

In the current study, *E. coli* was utilized to gauge the effectiveness of the prepared nanoparticles. The antibacterial potential of the prepared NPs is shown Figure 10 a, b, c, d. In addition, 100 µl of each nanoparticle concentration (5, 10 and 20 mg/mL) was used to treat *E. coli* and the inhibition zone (ZOI) was measured. The maximum ZOI was 22.1 mm at 20 mg/mL, followed by followed by 17.4 mm at 10 mg/mL and 10.2 mm at 5 mg/mL (Figure 10a, b, c, d). The comparative antibacterial activity of the prepared nanoparticles with previously work is described in Table 5. In antibacterial activity, membrane is the main protective impediments to bacterial fight from the outer agent. The greater surface to volume ratio ZnO nanoparticles, leading to the creation of more reactive ions. Zinc oxide nanoparticles depict better anti-microbial action as compared to soluble Zn compounds like Zinc chloride because of their active targeting potential, the ability for its generation in the cell membrane and thus, disruption of cell membrane integrity and ROS generation capacity which further aids in protein, lipid, and DNA denaturation (Muthuvel et al. 2020). Scientists have Reported that the effect of ZnO NP on *C. jejuni* bacterial culture was bactericidal and not bacteriostatic as they observed no recovery of the bacterial cell (Al Rugaie et al. 2022). Cell membrane blebbing and leakage is considered as one of the main mechanisms of inhibitory effect of nanoparticles on bacteria. Internalization of ZnO NP leads to integrity loss of phospholipid bilayer and leakage of intracellular components like lipopolysaccharide and ATP out of the cell ultimately leading to cell death. E. Brayner et al. reported cell membrane integrity loss as the major cause of bactericidal effect of ZnO NP on *E. coli* cell (Zhang et al. 2023). Nanoparticle attachment and inclusion alter the resting membrane potential of the cell membrane and induces depolarization of cell membrane by blocking K^+ ion channel present in the cell membrane (Dadi et al. 2019). Zeta potential measurement i.e. measurement of charge of the bacterial surface can be used as a marker for the estimation of membrane damage (Yassin et al. 2023). A large number of proteins upregulate its expression upon exposure to zinc oxide nanoparticle leading to lipid peroxidation (Mthana et al. 2023). Nanoparticles interact with membrane proteins and inactivate them decreasing membrane permeability and causing cell death. Zn²⁺ that is released by ZnO NPs may induce a conformational change in the enzyme and caused the distortion of the active site of enzyme and block the activity of bacterial cell which leads the main cause of bacterial inhibition (Modi et al., 2023). In our results the antibacterial activity was enhanced with ZnO concentration which are aligned to the earlier studies (Yin et al. 2023).




Figure 10. Antibacterial activity of the ZnONPs

Antifungal assay

The antifungal potential of ZnO NPs using PDA containing petri plates were studied Figure 11a, b, c, d. The highest growth inhibition ($85 \pm 2.1\%$) was observed at a 1 mg/mL, followed by a 0.75 mg/mL dosage rate ($66 \pm 1.7\%$) and 0.50 mg/mL (56.77 ± 0.5). Additional rising in ZnO NPs dosage did not increase further inhibition, because increase in dosage leads to clump development of the NPs. Nanoparticles have a smaller size but greater surface area, makes the NPs more reactive and stable (Takcı et al. 2023). The physiochemical properties, like size, Brownian movement, and surface charge, might also have an influence on the accretion. From the last decade, mycologists have efficiently used ZnO NPs to retard the growth of different fungal pathogens, including *Fusarium graminearum*, *Candida albicans*, and *Aspergillus niger* (Hosseini et al. 2023). Previous works suggest that antifungal potential of MO-NPs is because of reactive oxygen species production. It is also reported that nano material can interact powerfully to the microbial wall and thus shows antimicrobial activity (Eldeeb et al. 2024). Metal oxide NPs creates pores in the wall and disturb the structure of the plasma membrane such as the depolarization, disturbs the fluidity and permeability of the membrane, consequently, arrive the cytoplasm without any hindrance, and leads to the DNA, RNA, and proteins disruption (Kalpana et al. 2018). This disruption causes the seepage of various materials like RNA, proteins, DNA and enzymes resulting in cell demise. The whole mechanism of antimicrobial potential is depicted in Figure 12.




Figure 11. Antibacterial activity of the ZnONPs




Figure 12. Schematic diagram of the whole study

Assessment of the ZnO in Cd adsorption

Effect of connection time and adsorption kinetics

Contact time is a key element in adsorption of metal by the nanosorbent in the waste water treatment. Adsorption indicates the accumulation of sorbates or solutes at the surface or interface of solid substrates (Housseiny et al. 2019, Eleryan et al. 2022). Therefore, an inclusive study was conducted to explore the impact of contact time on the process of adsorption from 5 to 120 minutes. In the start the rate of adsorption was high as depicted in the Figure 13 which may be due to the free reactive places on the surface of ZnO NPs (Aigbe et al. 2022, Kumari et al. 2015). With increasing in the contact time between Cd and ZnO, the adsorption efficacy greatly enhances due to the increased interaction between Cd and active sites. Highest adsorption was 85.3 mg/g contact time of at 120 mins. These results display that ZnO NPs have efficient adsorption ability and are excellent adsorbent in the Cd removal. Results of our study parallel with the former work conducted for the elimination of pollutants (Okpara et al. 2020, Manzoor et al. 2016, Yang et al.2019).




Figure 13. Rate of adsorption of the pollutants via ZnONPs

Kinetic study is basic approach to assess the efficacy against the environmental pollutants A detailed kinetics study was conducted on the adsorption Cd ions by applying different kinetic models, including the pseudo-first-order ($P^{1st}OK$), and pseudo-second-order kinetic models ($P^{2nd}OK$). As presented in Figure 14 a and b.

Pseudo first order kinetics depends upon the weak forces between the ZnO NPs and Cd mainly ruled by physisorption forces (Eleryan et al.2023). The linear form of ($P^{1st}OK$) is presented in formula (9)

$$\ln(q_e - q_t) = \ln q_e - K_1 t \quad (9)$$

Where q_t refers to the amount of Cd at a particular time, q_e is the amount of Cd onto the adsorbent at equilibrium. The rate constant linked with $P^{1st}OK$ is designated by the parameter K_1 (1/min). This study comprises plotting $\log(q_e - q_t)$ against time (t) to obtained the rate constant and correlation coefficient for the $P^{1st}OK$.

$P^{2nd}OK$ model mainly controls chemisorption interaction (Hoseinzadeh et al. 2016). Following formula was applied mathematical representation of $P^{2nd}OK$.

$$\frac{t}{q_t} = \frac{1}{K_2 q_e^2} + \frac{1}{q_e} t \quad (10)$$

The $P^{2nd}OK$ rate constant, represented as K_2 , is calculated by drawing a plot t/q_t versus (t).

Significantly greater correlation coefficient (R^2) was attained from the P^{2nd}OK model to that of the other kinetic model gives confirmation the adsorption kinetics was administered via the P^{2nd}OK model (Table 6). This designates that the rate-regulating phase in the Cd adsorption onto the ZnO NPs was chemisorption mechanisms. All these findings are consistent with previously published studies (Zhang et al., 2014, Nguyen et al. 2019, Jain et al. 2018).




Figure 14. Assessment of the mechanism through kinetic model.

Impact of initial metals concentrations on adsorption

Figure 15 shows the impact of the primary concentrations of metals ranging from 20 to 120 mg/L on the Cd adsorption onto ZnO NPs. It was concluded that Cd adsorption enhanced with rising initial concentration of Cd. The maximum Cd absorption (80.3 mg/g) was perceived at highest Cd concentration (120 mg/L). The results of the, increase in metals concentration, the adsorption efficiency of nanoparticles was enhanced all exactly parallel to previous study conducted on the adsorption by using organic based substances (Ameh et al. 2023, Dubeyet al. 2016).

One of the aims of the current study was to apply Freundlich, and Langmuir, isotherm models on adsorption data. When the solid and liquid phases are in equilibrium, the Langmuir model depicts the distribution of metal ions and measures the creation of an adsorbate monolayer on the adsorbent's surface (Ho & McKay 1998). Equations designated below applied to determine the parameters required to elucidate these isotherm models:

Langmuir isotherm model

$$\frac{1}{q_e} = \frac{1}{K_L q_{\max}} \cdot \frac{1}{C_e} + \frac{1}{q_{\max}} \quad (11)$$

$$R_L = \frac{1}{1 + C_i \times K_L}$$

K_L denotes Langmuir constant, R_L shows separation factor, and q_{\max} is the highest adsorption potential

Freundlich isotherm is appropriate for elaborating multilayer adsorption surfaces that show heterogeneity (Kaewsarn et al. 2002). The equation 10 shows the Freundlich adsorption isotherm:

$$\text{Log}q_e = \text{Log}K_f + \frac{1}{n} \text{log}C_e \quad (12)$$

K_f shows Freundlich's constant, and $1/n$ refers to intensity adsorption.

Plots of isotherm study are shown in Figures 16a, and 16b, and the conforming isotherm constants and correlation coefficients are described in Table 7. Attained findings show that the Langmuir model exhibit a remarkably greater R^2 value in comparison to that of isotherm model, suggesting its more suitable to the data of adsorption Cd and supporting the adsorbent surface homogeneity. Adsorption isotherm revealed a well-fitted Langmuir isotherm at high residual concentrations of Cd in the solution phase, indicating a declination of adsorbents active sites (Aigbe et al. 2022, Kumari et al. 2015). Highest adsorption potential of ZnO NPs was assessed with the Langmuir isotherm as 85.6898 mg/g. Moreover, the Freundlich model borne $1/n$ between 0 and 1 (0. 0.3013 for Cd). The Values of $1/n$ less unity gives confirmation of the efficient adsorption was done (Chanani et al 2023, (Ho & McKay 1998). Results of the current study recommend that the adsorption process closely align to the Langmuir model.




Figure 15. Impact of the primary concentrations of metals




Figure 16. Plots of isotherm study

Conclusion

Interest in green technology has increased because of the of non-toxic substances and development of effective, economical, and eco-friendly materials. This study intended on preparation of ZnO nanoparticles through the eco-friendly procedure using A.

nilotica leaf extract. The inspired ZnO NPs were efficaciously characterized through different microscopic and spectroscopic techniques and used in biomedical and environmental assays. The prepared NPs were assessed for antioxidant activities, antibacterial, antifungal activity, anti-inflammatory and anti-leishmanial activity. Lastly, the ZnO NPs were assessed for the and environmental application against the Cd adsorption. ZnO NPs displayed the efficient potential to adsorb Cd. Inclusive, our study show that the bio-fabricated ZnO NPs may work as a true candidate for biological and environmental applications for the removal of chemicals from contaminated water and metals sewage treatment. Conspicuously, the applied procedure is green, clean and natural without the consumption of any risky materials. However, despite the promising advancements, several challenges remain to be addressed. Future research efforts should focus on developing sustainable synthesis routes for nanoparticles, improving their stability, enhancing their targeted delivery to specific sites in the body, and minimizing adverse effects on human health. Furthermore, in the coming years, interdisciplinary collaborations between scientists and policymakers will be crucial for unlocking the full potential of nanoparticles and addressing societal challenges. By addressing the existing limitations and harnessing the opportunities offered by nanoparticles, we can pave the way for a more sustainable, efficient, and technologically advanced future.

Authors contributions

Saifullah Khan conceptualized the study, designed the methodology, and supervised the overall research work. Mohsin Ali and Kainat Qureshi contributed to data collection, experimental work, and initial drafting of the manuscript. Shah Naeem and Fatima Hayat were involved in data analysis, interpretation of results, and preparation of figures and tables. M. Hisham Al Nasir provided critical review, technical guidance, and validation of experimental procedures. Saher Naveed and Saima Sher Afghan contributed to literature review, editing, and formatting of the manuscript. Muhammad Imran assisted in statistical analysis and manuscript revision. Rida Nisar contributed to proofreading, final editing, and coordination among all authors. All authors have read and approved the final version of the manuscript.

Data Availability Statement: Not Pertinent.

Conflicts of Interest: All the authors affirm that we don't have any conflict among us.

Reference

- BHILKAR PR., BODHNE AS, YERPUDE, ST, MADANKAR R, SOMKUWAR, SR, CHAUDHARY AR, LAMBAT A, DESIMONE M, SHARMA R, & CHAUDHARY RG. 2023. Phyto-derived metal nanoparticles: Prominent tool for biomedical applications. *Open Nano*, p100192.
- PERWEZ M, LAU SY, HUSSAIN D, ANBOO S, ARSHAD M, & THAKUR P. 2023. Nanozymes and nanoflower: Physiochemical properties, mechanism and biomedical applications. *Colloids Surf B Biointer*, 225, 113241.
- RAVINDRAN A, CHANDRAN P, & KHAN SS. 2013. Biofunctionalized silver nanoparticles: advances and prospects. *Colloids Surf B Biointer*, 105, 342-352.
- KHALAFI T, BUAZAR F, & GHANEMI, K. 2019. Phycosynthesis and enhanced photocatalytic activity of zinc oxide nanoparticles toward organosulfur pollutants. *Sci. Rep*, 9(1), 6866.
- CHANANI J, BUAZAR F, & NIKPOUR Y. 2023. Promoted photocatalytic activity of green titanium oxide-clay nanocomposite toward polychlorinated biphenyl degradation in actual samples. *Water, Air, & Soil Pollut*, 234(6), 364.

- BUAZAR F, SAYAHI MH, & ZAREI SEFIDDASHTI A. 2023. Marine carrageenan-based NiO nanocatalyst in solvent-free synthesis of polyhydroquinoline derivatives. *Appl. Organomet. Chem*, 37(9), e7191.
- RAHIMI S, BUAZAR, F, & LARKI, A. 2023. Efficient absorption and sensing of haloacetonitriles on fullerene C₂₀ surface at DFT Level. *Water, Air, & Soil Pollut*, 234(7), 409.
- SAFARI N, GHANEMI, K, & BUAZAR F. 2020. Selenium functionalized magnetic nanocomposite as an effective mercury (II) ion scavenger from environmental water and industrial wastewater samples. *J. Environ. Manag*, 276, 111263.
- PANTIDOS N, & HORSFALL LE. 2014. Biological synthesis of metallic nanoparticles by bacteria, fungi and plants. *J. of Nanomed. & Nanotechnol*, 5(5), 1.
- SIDDIQI KS, & HUSEN A. 2016. Fabrication of metal nanoparticles from fungi and metal salts: scope and application. *Nanoscale Res. Lett*, 11, 1-15.
- Moavi J, Buazar F, & Sayahi MH. 2021. Algal magnetic nickel oxide nanocatalyst in accelerated synthesis of pyridopyrimidine derivatives. *Sci. Rep*, 11(1), 6296.
- WANG X, XIE H, WANG P, & YIN H. 2023. Nanoparticles in plants: uptake, transport and physiological activity in leaf and root. *Matt*, 16(8), 3097.
- KHALAFI T, BUAZAR, F, & GHANEMI K. 2019. Phycosynthesis and enhanced photocatalytic activity of zinc oxide nanoparticles toward organosulfur pollutants. *Sci. Rep*, 9(1), 6866.
- BUAZAR F, BAGHLANI-NEJAZD MH, BADRI M, KASHISAZ M, KHALEDI-NASAB A, & KROUSHAWI, F. 2016. Facile one-pot phytosynthesis of magnetic nanoparticles using potato extract and their catalytic activity. *Starch-Stärk*, 68(7-8), 796-804.
- KOOPI H, & BUAZAR F. 2018. A novel one-pot biosynthesis of pure alpha aluminum oxide nanoparticles using the macroalgae *Sargassum ilicifolium*: a green marine approach. *Ceram. Int.*, 44(8), 8940-8945.
- BUAZAR F, SAYAHI MH, & ZAREI SEFIDDASHTI A. 2023. Marine carrageenan-based NiO nanocatalyst in solvent-free synthesis of polyhydroquinoline derivatives. *Appl. Organomet. Chem*, 37(9), e7191.
- Liaqat M, Younas A, Iqbal T, Afsheen S, Zubair M, Kamran SKS, & Wong LS. 2024. Synthesis and characterization of ZnO/BiVO₄ nanocomposites as heterogeneous photocatalysts for antimicrobial activities and waste water treatment. *Mater. Chem. Phys.*, 315, 128923.
- CAMPAÑA AL, SARAGLIADIS A, MIKHEENKO P, & LINKE D. 2023. Insights into the bacterial synthesis of metal nanoparticles. *Front. nanotechnol*, 5, 1216921.
- ALAVI M, & NOKHODCHI, A. 2021. Synthesis and modification of bio-derived antibacterial Ag and ZnO nanoparticles by plants, fungi, and bacteria. *Drug Discov. Today*, 26(8), 1953-1962.
- Elmaghraby NA, Hassaan MA, Zien MA, Abedelrhim EM, Ragab S, Yılmaz M, & El Nembr A. 2024. Fabrication of carbon black nanoparticles from green algae and sugarcane bagasse. *Sci. Rep*, 14(1), 5542.
- SABOURI Z, SABOURI S, MOGHADDAS SSTH, MOSTAFAPOUR A, GHEIBIHAYAT SM, & DARROUDI, M. 2022. Plant-based synthesis of Ag-doped ZnO/MgO nanocomposites using *Caccinia macranthera* extract and evaluation of their photocatalytic activity, cytotoxicity, and potential application as a novel sensor for detection of Pb²⁺ ions. *Biomass Convers. Biorefin.*, 1-13.
- ZAFAR M, & IQBAL T. 2024. Green synthesis of silver and zinc oxide nanoparticles for novel application to enhance shelf life of fruits. *Biomass Convers. Biorefin.*, 14(4), 5611-5626.

- TORTELLA G, RUBILAR O, PIERETTI JC, FINCHEIRA P, DE MELO SANTANA B, FERNÁNDEZ-BALDO M. A, & SEABRA AB. 2023. Nanoparticles as a promising strategy to mitigate biotic stress in agriculture. *Antibiot.*12(2), 338.
- GUERRINI L, ALVAREZ-PUEBLA RA, & PAZOS-PEREZ N. 2018. Surface modifications of nanoparticles for stability in biological fluids. *Mattr*, 11(7), 1154.
- ALI A, PHULL AR, & ZIA M. 2018. Elemental zinc to zinc nanoparticles: Is ZnO NPs crucial for life? Synthesis, toxicological, and environmental concerns. *Nanotechnol. Rev.*7(5), 413-441.
- NADHIYA D, KALA A, SANDHIYA V, THIRUNAVUKKARASU P, KARNAN C, PRABHAHARAN M, & SULAIMAN, GM. 2023. Influence of Annealing Temperature on Structural, Morphological, Optical, Magnetic, and Antimicrobial Properties of Zinc Ferrite Nanoparticles. *Plasmon*, 1-11.
- NEOLAKA YA., LAW A Y, RIWU M, DARMOKOESOEMO H, SETYAWATI H, NAAT J, & KUSUMA, HS. 2022. Synthesis of Zinc (II)-natural zeolite mordenite type as a drug carrier for ibuprofen: Drug release kinetic modeling and cytotoxicity study. *Results Chem.* 4, 100578.
- ELERYAN A, AIGBE UO, UKHUREBOR KE, ONYANCHA RB, HASSAAN MA, ELKATORY MR, & EL NEMR A. 2023. Adsorption of direct blue 106 dye using zinc oxide nanoparticles prepared via green synthesis technique. *Environ Sci Pollut Res*, 30(26), 69666-69682.
- RAHA S, & AHMARUZZAMAN M.2022. ZnO nanostructured materials and their potential applications: progress, challenges and perspectives. *Nanoscale Adv.*, 4(8), 1868-1925.
- VERMA R, PATHAK S, SRIVASTAVA AK, PRAWER S, & TOMLJENOVICHANIC S. 2021. ZnO nanomaterials: Green synthesis, toxicity evaluation and new insights in biomedical applications. *J. Alloys Compd.*, 876, 160175.
- THEERTHAGIRI J, SALLA S, SENTHIL RA, NITHYADHARSEN P, MADANKUMAR A, ARUNACHALAM P, & KIM HS. 2019. A review on ZnO nanostructured materials: energy, environmental and biological applications. *Nanotechnol*, 30(39), 392001.
- PILLAI AM, SIVASANKARAPILLAI, VS, RAHDAR A, JOSEPH J, SADEGHFAR F, RAJESH K, & KYZAS GZ. (2020). Green synthesis and characterization of zinc oxide nanoparticles with antibacterial and antifungal activity. *J. Mol. Struct*, 1211, 128107.
- LI X, DU W, XU W, LING G, & ZHANG P. 2023. Dissolving microneedles based on ZnO nanoparticles and an ionic liquid as synergistic antibacterial agents. *J. Mater. Chem. B*, 11(19), 4354-4364.
- MURALI M, GOWTHAM HG, SHILPA N, SINGH SB, AIYAZ M, SAYYED RZ, & KOLLUR, SP. 2023. Zinc oxide nanoparticles prepared through microbial mediated synthesis for therapeutic applications: A possible alternative for plants. *Front. microbiol*, 14, 1227951.
- El-Nemr MA, Aigbe UO, Ukhurebor KE, Onyancha RB, El Nemr A, Ragab, S, & Hassaan, MA.2022. Adsorption of Cr⁶⁺ ion using activated Pisum sativum peels-triethylenetetramine. *Environ Sci Pollut Res*, 29(60), 91036-91060.
- BUJANG A, RAHMAN FA, & OMAR SRS. 2020. Nanotechnology in the food processing and packaging: an overview of its halalan tayyiban aspect. *Malaysian J Consum Fam Econ*, 24, 1-14.
- NELSON M. 2018. A study of urban vegetable garden and their soils in Corvallis and Portland.
- ONYANCHA RB, AIGBE UO, UKHUREBOR KE, KUSUMA HS, DARMOKOESOEMO H, OSIBOTE, OA, & PAL K. 2022. Influence of magnetism-mediated potentialities of recyclable adsorbents for heavy metal

- ions removal from aqueous solutions—an organized review. *Results Chem*, 4, 100452.
- NEOLAKA YA, RIWU AA, AIGBE, UO, UKHUREBOR, KE, ONYANCHA RB, DARMOKOESOEMO H, & KUSUMA HS. 2023. Potential of activated carbon from various sources as a low-cost adsorbent to remove heavy metals and synthetic dyes. *Results Chem.*, 5, 100711.
- ELDEEB TM, AIGBE UO, UKHUREBOR KE, ONYANCHA RB, EL-NEMR MA, HASSAAN MA, & EL NEMR A. 2024. Adsorption of methylene blue (MB) dye on ozone, purified and sonicated sawdust biochars. *Biomass Convers. Biorefin*, 14(8), 9361-9383.
- BAIRAGI S, & KAMALI MR. 2023. Review on green biomass-synthesized metallic nanoparticles and composites and their photocatalytic water purification applications: Progress and perspectives. *Chem. Eng. J. Adv.*, 14, 100460.
- DHIMAN V, & KONDAL N. 2021. ZnO Nanoadsorbents: A potent material for removal of heavy metal ions from wastewater. *J. Colloid Interface Sci.*, 41, 100380.
- OZKAN G, KAMILOGLU S, OZDAL T, BOYACIOGLU, D, & CAPANOGLU E. 2016. Potential use of Turkish medicinal plants in the treatment of various diseases. *Mol*, 21(3), 257.
- KOPARDE AA, MAGDUM CS, & DOJAD RC. 2017. Phyto active compounds from herbal plant extracts: its extraction, isolation and characterization. *World J. Pharm. Res.*, 6(8), 1186-1205.
- HASHIM S, AYUB S, JAN A, ISRAR M, KHAN MA, & FAWAD M. 2022. medicinal properties, phytochemistry and pharmacology of *Acacia modesta* (Wall.) Hurt. *Pak. J. Weed Sci. Res*, 28(3).
- KHANUM H, ISHTIAQ M, BHATTI KH, HUSSAIN I, AZEEM M, MAQBOOL M, & SAYED S. 2022. Ethnobotanical and conservation studies of tree flora of Shiwalik mountainous range of District Bhimber Azad Jammu and Kashmir, Pakistan. *PloS one*, 17(2), 0262338.
- GHAURI H, ZAHRA Q, RAZA J, HAMMAD RM, ELSADEK MF, ALMOAJEL A, & SHIREEN F. 2023. Synthesis, characterization and biological investigation of zinc nanoparticles using *Acacia modesta* Wall. leaves. *Pak. J. pharmace. Sci.*, 36(3), 981-987.
- SALEEM B, ISLAM M, SAEED H, IMTIAZ F, ASGHAR M, SALEEM Z, & NAHEED S. 2018. INVESTIGATIONS OF ACACIA MODESTA WALL. leaves for in vitro anti-diabetic, proliferative and cytotoxic effects. *Braz. J. Pharm.*, 54.
- ARBAB AH, PARVEZ MK, AL-DOSARI MS, AL-REHAILY AJ, AL-SOHAIBANI M, ZAROUG EE, & RAFATULLAH, S. 2015. Hepatoprotective and antiviral efficacy of *Acacia mellifera* leaves fractions against hepatitis B virus. *Biomed Res. Int*, 2015.
- BUKHARI IA, KHAN RA, GILANIAH, AHMED S, & SAEED, SA. 2010. Analgesic, anti-inflammatory and anti-platelet activities of the methanolic extract of *Acacia modesta* leaves. *Inflammopharmacol*, 18, 187-196.
- ULLAH S, JAN G, GUL F, KHAN S, KHATTAK M, IHSAN M, & BIBI H. 2018. Phytochemical and nutritional analysis of selected plants of district Buner Pakistan. *Int. J. Fauna Biol.*, 5(3), 111-117.
- ABID F, SALEEM M, MULLER CD, ASIM MH, ARSHAD S, MAQBOOL T, & HADI F. 2020. Anti-proliferative and apoptosis-inducing activity of *Acacia modesta* and *Opuntia monacantha* extracts on HeLa cells. *APJCP*, 21(10), 3125.
- SHARMILA G, THIRUMARIMURUGAN, M, & MUTHUKUMARAN C. 2019. Green synthesis of ZnO nanoparticles using *Tecoma castanifolia* leaf extract:

- Characterization and evaluation of its antioxidant, bactericidal and anticancer activities. *Microchem. J.*, 145, 578-587.
- KAMAL ASIF, UROOJ HAROON, HAKIM MANGHWAR, KHALID HALMER, IBTISAM MALSUDAS, ASHWAQ TALHOBAlTI, ANILA IQBAL, MAHNOOR AKBAR, FARHANA, MARYAM ANAR, MOONA NAZISH, HASSAN JAVED CHAUDHARY, MUHAMMAD FAROOQ HUSSAIN MUNIS. 2022. Biological Applications of Ball-Milled Synthesized Biochar-Zinc Oxide Nanocomposite Using *Zea mays* L. *Mol.*, 27(16):5333.
- HOUSSEINY MANAL MAHER, & EMAN ZAKARIA GOMAA. 2019. Enhancement of antimicrobial and antitumor activities of zinc nanoparticles biosynthesized by *Penicillium chrysogenum* AUMC 10608 using gamma radiation. *Egypt. J. Bot.* 59(2):319-337.
- FADWA AO, ALKOBLAN DK, MATEEN A, & ALBARAG AM. 2021. Synergistic effects of zinc oxide nanoparticles and various antibiotics combination against *Pseudomonas aeruginosa* clinically isolated bacterial strains. *Saudi J. Biol. Sci.*, 28(1), 928-935.
- MUHAMMAD W, ULLAH N, HAROON M, & ABBASI BH. 2019. Optical, morphological and biological analysis of zinc oxide nanoparticles (ZnO NPs) using *Papaver somniferum* L. *RSC advan*, 9(51), 29541-29548.
- Arora AK, Devi S, Jaswal VS, Singh J, Kinger M, & Gupta VD. 2014. Synthesis and characterization of ZnO nanoparticles. *Oriental Journal of Chemistry*, 30(4), 1671-1679.
- EL-BELELY EF, FARAG MM, SAID HA, AMIN AS, AZAB E, GOBOURI AA, & FOU DA A. 2021. Green synthesis of zinc oxide nanoparticles (ZnO-NPs) using *Arthrospira platensis* (Class: Cyanophyceae) and evaluation of their biomedical activities. *Nanomat.*, 11(1), 95.
- KAUSHIK M, NIRANJAN R, THANGAM R, MADHAN B, PANDIYARASAN V, RAMACHANDRAN C, & VENKATASUBBU, GD. 2019. Investigations on the antimicrobial activity and wound healing potential of ZnO nanoparticles. *Appl. Surf. Sci.*, 479, 1169-1177.
- EMAMI-KARVANI, Z, & CHEHRAZI P. 2011. Antibacterial activity of ZnO nanoparticle on gram-positive and gram-negative bacteria. *Afr. J. Microbiol Res*, 5(12), 1368-1373.
- KASHYP K, DAS AK, BHARDWAJ AK., ROYMAHAPATRA G, GHOSH A, HIAT M, & JAIN R. 2023. Phytochemical analysis of *Careya arborea* roxb. root extracts: a qualitative analytical approach. *ES Gen.*, 1, 959.
- NIAZ M, ABRAR H, JADOON R, AKRAM K, QAYYUM H, ASHFAQ S, & SULTAN A. 2023. Qualitative phytochemical analysis of stem, leaves and fruits of *Withania somnifera* L. in different solvents. *Phytopharm. Res. J.* 2(3), 17-21.
- BUAZAR F, SAYAHI MH, & ZAREI SEFIDDASHTI A. 2023. Marine carrageenan-based NiO nanocatalyst in solvent-free synthesis of polyhydroquinoline derivatives. *Appl. Organomet. Chem.*, 37(9), e7191.
- Torfi-Zadegan, S, Buazar F, & Sayahi MH. 2023. Accelerated sonosynthesis of chromeno [4, 3-b] quinoline derivatives via marine-bioinspired tin oxide nanocatalyst. *Appl. Organomet. Chem.*, 37(12), e7286.
- CHIKKANNA MAHESH MIDATHARAHALLI, SHIVAYOGESWAR E, NEELAGUND, & KOTRESH K. RAJASHEKARAPPA. 2019. Green synthesis of zinc oxide nanoparticles (ZnO NPs) and their biological activity. *SN Appl. Sci.* 1: 1-10.
- ELUMALAI K, & VELMURUGAN S. 2015. Green synthesis, characterization and antimicrobial activities of zinc oxide nanoparticles from the leaf extract of *Azadirachta indica* (L.). *Appl. Surf. Sci.*, 345, 329-336.

- JIANG J, OBERDÖRSTER G BISWAS. 2009. Characterization of size, surface charge, and agglomeration state of nanoparticle dispersions for toxicological studies. *J. Nanopart. Res.*, 11, 77–89.
- DUBEY SP, DWIVEDI AD, LAHTINEN M, LEE C, KWON YN, SILLANPAA M. 2013. Protocol for development of various plants leaves extract in single-pot synthesis of metal nanoparticles. *Spectrochim. Acta Part A Mol. Biomol. Spectrosc.*, 103, 134–142.
- DE JESUS OLIVEIRA AC, DE ARAÚJO AR, QUELEMES PV, NADVORNY D, SOARES-SOBRINHO JL, DE ALMEIDA LEITE JR, DA SILVA-FILHO EC, DA SILVA DA. 2019. Solvent-free production of phthalated cashew gum for green synthesis of antimicrobial silver nanoparticles. *Carbohydr. Polym.*, 213, 176–183.
- SINGH K, CHOPRA DS, SINGH D, SINGH N. 2020. Optimization and ecofriendly synthesis of iron oxide nanoparticles as potential antioxidant. *Arab. J. Chem.*, 13, 9034–9046.
- SUMAIRA SIDDIQUE AFRIDI M, SALMAN HASHMI S, ALI GS, ZIA M, & HAIDER ABBASI B. 2018. Comparative antileishmanial efficacy of the biosynthesised ZnO NPs from genus *Verbena*. *IET nanobiotechnol.*, 12(8), 1067-1073.
- ABBASI BH., ANJUM S, & HANO C. 2017. Differential effects of in vitro cultures of *Linum usitatissimum* L. (Flax) on biosynthesis, stability, antibacterial and antileishmanial activities of zinc oxide nanoparticles: A mechanistic approach. *RSC advac.*, 7(26), 15931-15943.
- AGARWAL H, & SHANMUGAM V. 2020. A review on anti-inflammatory activity of green synthesized zinc oxide nanoparticle: Mechanism-based approach. *Bioinorg. Chem.*, 94, 103423.
- Sarkar J, Ghosh M, Mukherjee A, Chattopadhyay D, & Acharya K. 2014. Biosynthesis and safety evaluation of ZnO nanoparticles. *Bioprocess Biosyst. Eng.*, 37, 165-171.
- JANAKI AC, SAILATHA E, & GUNASEKARAN S. 2015. Synthesis, characteristics and antimicrobial activity of ZnO nanoparticles. *Spectrochim Acta A Mol Biomol Spectrosc.*, 144, 17-22.
- UL-HAQ I, ULLAH, BIBI G, KANWAL S, AHMAD MS, MIRZA B. 2012. Antioxidant and cytotoxic activities and phytochemical analysis of *Euphorbia wallichii* root extract and its fractions. *Iran. Jour. of pharm. Res.* 2012, 11, 241.
- KHAN AU, KHAN HU, ALHAR MSO, TAHIR K, ALMARHOON ZM, ZAKI ME, & KHAN AU. 2023. Antimicrobial, antioxidant, and antileishmanial activity of *Tavernier glabra* mediated ZnO NPs and Fe₂O₃ NPs. *Inorg. Chem. Commun*, 148, 110297.
- SALEH F, KHEIRANDISH F, ABBASI M, AHMADPOUR F, VEISKARAMI S, & MIRDERIKVAND A. 2024. Comparison of biosynthetic zinc oxide nanoparticle and glucantime cytotoxic effects on *Leishmania major* (MRHO/IR/75/ER). *J. Basic Microbiol.*
- ABBASI BH, ANJUM S, & HANO C. 2017. Differential effects of in vitro cultures of *Linum usitatissimum* L. (Flax) on biosynthesis, stability, antibacterial and antileishmanial activities of zinc oxide nanoparticles: A mechanistic approach. *RSC advan.*, 7(26), 15931-15943.
- NAZIR S, RABBANI A, MEHMOOD K, MAQBOOL F, SHAH GM, KHAN MF, & SAJID M. 2019. Antileishmanial activity and cytotoxicity of ZnO-based nano-formulations. *Inter. J. of Nanomed.*, 7809-7822.
- ABDULAZEEM L, ALASMARI AF, ALHARBI M, ALSHAMMARI A, & MUHSEEN ZT. 2023. Utilization of aqueous broccoli florets extract for green synthesis and characterization of silver nanoparticles, with potential biological applications. *Heliyo.*, 9(9).

- NAGAJYOTHI PC, CHA SJ, YANG IJ, SREEKANTH TVM, KIM KJ, & SHIN HM. 2015. Antioxidant and anti-inflammatory activities of zinc oxide nanoparticles synthesized using *Polygala tenuifolia* root extract. *J. Photochem. Photobiol. B: Biol*, 146, 10-17.
- DEVI BV, RAJASEKAR AR. & RAJESHKUMAR S. 2020. Antiinflammatory activity of zinc oxide nanoparticles synthesised using grape seed extract: An in vitro study. *Plant Cell Biotechnol Mol Biol*, 21(33-34), 6-16.
- RANGEELA M, RAJESHKUMAR S, LAKSHMI T, & ROY A. 2019. Anti-inflammatory activity of zinc oxide nanoparticles prepared using amla fruits. *Drug Discov. Today*, 11(10).
- MINHAS LA, KALEEM M, JABEEN A, ULLAH N, FAROOQI HMU, KAMAL A, & MUMTAZ AS. 2023. Synthesis of Silver Oxide Nanoparticles: A Novel Approach for Antimicrobial Properties and Biomedical Performance, Featuring *Nodularia haraviana* from the Cholistan Desert. *Microorgan.*, 11(10), 2544.
- SIRIPIREDDY B, & MANDAL BK. 2017. Facile green synthesis of zinc oxide nanoparticles by *Eucalyptus globulus* and their photocatalytic and antioxidant activity. *Adv. Powder Technol.*, 28(3), 785-797.
- BHOSALE AS, ABITKAR KK, SADALAGE PS, PAWAR KD, & GARADKAR KM. 2021. Photocatalytic and antibacterial activities of ZnO nanoparticles synthesized by chemical method. *J. Electron. Mater.*, 32, 20510-20524.
- ARIF H, QAYYUM S, AKHTAR W, FATIMA I, KAYANI WK, RAHMAN KU, & ALI S. 2023. Synthesis and Characterization of Zinc Oxide Nanoparticles at Different pH Values from *Clinopodium vulgare* L. and Their Assessment as an Antimicrobial Agent and Biomedical Application. *Micromach.*, 14(7), 1285.
- MUTHUVEL A, JOTHIBAS M, & MANOHARAN C. 2020. Effect of chemically synthesis compared to biosynthesized ZnO-NPs using *Solanum nigrum* leaf extract and their photocatalytic, antibacterial and in vitro antioxidant activity. *J. Environ. Chem. Eng.*, 8(2), 103705.
- AL RUGAIE O, JABIR MS, MOHAMMED MK, ABBAS RH, AHMED DS, SULAIMAN GM, & MOHAMMED HA. 2022. Modification of SWCNTs with hybrid materials ZnO–Ag and ZnO–Au for enhancing bactericidal activity of phagocytic cells against *Escherichia coli* through NOX2 pathway. *Sci. Rep.* 12(1), 17203.
- ZHANG H, WANG X, YAN A, DENG J, XIE Y, LIU S, & XU J. 2023. Evolutionary analysis of respiratory burst oxidase homolog (RBOH) genes in plants and characterization of ZmRBOHs. *Int. J. Mol. Sci*, 24(4), 3858.
- DADI R, AZOUANI R, TRAORE M, MIELCAREK C, & KANAIEV A. 2019. Antibacterial activity of ZnO and CuO nanoparticles against gram positive and gram negative strains. *Mater. Sci. Eng. C*, 104, 109968.
- YASSIN, A. Y., ABDELGHANY, A. M., SALAMA, R. S., & TARABIAH, A. E. 2023. Structural, optical and antibacterial activity studies on CMC/PVA blend filled with three different types of green synthesized ZnO nanoparticles. *J. Inorg. Organomet. Polym. Mater*, 33(7), 1855-1867.
- MTHANA MS, MTHIYANE DM, ONWUDIWE DC, & SINGH M. 2022. Biosynthesis of ZnO nanoparticles using capsicum Chinense fruit extract and their in vitro cytotoxicity and antioxidant assay. *J. Appl. Sci.*, 12(9), 4451.
- Modi SK, Gaur S, Sengupta M, & Singh MS. 2023. Mechanistic insights into nanoparticle surface-bacterial membrane interactions in overcoming antibiotic resistance. *Front. microbiol.*, 14, 1135579.
- YIN S, LINKLATER DP, LI Z, ZHAO S, HE S, XIANG S, & SUN K. 2023. Translocation of Pyrimidine Derivative-Capped Gold Nanoparticles via Membrane Ion Channels Induce *Pseudomonas aeruginosa* and *Staphylococcus aureus* Cell Death. *ACS Mat. Lett.*, 6(2), 418-426.

- SUMMER M, ALI S, TAHIR HM, ABAIDULLAH R, FIAZ U, MUMTAZ S, & FAROOQ MA. 2024. Mode of Action of Biogenic Silver, Zinc, Copper, Titanium and Cobalt Nanoparticles Against Antibiotics Resistant Pathogens. *J. Inorg. Organomet. Polym. Mater*, 1-35.
- ALDEEN TS, MOHAMED HEA, & MAAZA M. 2022. ZnO nanoparticles prepared via a green synthesis approach: Physical properties, photocatalytic and antibacterial activity. *J phys chem solids*, 160, 110313.
- THI TUD, NGUYEN TT, THI YD, THI KHT, PHAN BT, & PHAM KN. 2020. Green synthesis of ZnO nanoparticles using orange fruit peel extract for antibacterial activities. *RSC advan.*, 10(40), 23899-23907.
- ELUMALAI K, & VELMURUGAN S. 2015. Green synthesis, characterization and antimicrobial activities of zinc oxide nanoparticles from the leaf extract of *Azadirachta indica* (L.). *Appl. Surf. Sci.*, 345, 329-336.
- EL-KHAWAGA AM, ELSAYED MA, GOBARA M, SULIMAN AA, HASHEM AH, ZAHER AA, & SALEM SS. 2023. Green synthesized ZnO nanoparticles by *Saccharomyces cerevisiae* and their antibacterial activity and photocatalytic degradation. *Biomass Convers. & Biorefin.*, 1-12.
- ODONGO EA, MUTAI PC, AMUGUNE BK, MUNGAI NN, AKINYI MO, & KIMONDO J. 2023. Evaluation of the antibacterial activity of selected Kenyan medicinal plant extract combinations against clinically important bacteria. *BMC complement. med. ther.*, 23(1), 100.
- TAKCI DK, OZDENEFE MS, & GENC S. 2023. Green synthesis of silver nanoparticles with an antibacterial activity using *Salvia officinalis* aqueous extract. *J. Cryst. Growth*, 614, 127239.
- Hosseini M, Soudi MR, Tajer-Mohammad-Ghazvini P, & Tavakoli HZ. 2023. Uranium biosorption by autolyzed residues of baker yeast: characterization and optimization. *Biomass Convers. and Bioref.*, 1-16.
- ELDEEB TM, AIGBE UO, UKHUREBOR KE, ONYANCHA RB, EL-NEMR MA, HASSAAN MA, & EL NEMR A. 2024. Biosorption of acid brown 14 dye to mandarin-CO-TETA derived from mandarin peels. *Biomass Convers. and Bioref.*, 14(4), 5053-5073.
- VN KALPANA, BAS KATARU, N SRAVANI, T VIGNESHWARI, A PANNEERSELVAM, V DEVI RAJESWARI. 2018. Biosynthesis of zinc oxide nanoparticles using culture filtrates of *Aspergillus niger*: Antimicrobial textiles and dye degradation studies. *Open Nano.*, 3:48-55.
- HOUSSEINY MM, & EMAN Z. 2019. Enhancement of antimicrobial and antitumor activities of zinc nanoparticles biosynthesized by *Penicillium chrysogenum* AUMC 10608 using gamma radiation. *Egypt. J. Bot.* 59(2):319-337.
- ELERYAN A, AIGBE UO, UKHUREBOR KE, ONYANCHA RB, ELDEEB TM, EL-NEMR MA, & EL NEMR A. 2022. Copper (II) ion removal by chemically and physically modified sawdust biochar. *Biomass Convers. Biorefin*, 1-38.
- AIGBE UO, UKHUREBOR KE, ONYANCHA, RB, OKUNDAYE B, PAL K, OSIBOTE OA, & DARMOKOESOEMO H. 2022. A facile review on the sorption of heavy metals and dyes using bionanocomposites. *Adsorp. Sci. & Technol*, 2022, 1-36.
- KUMARI R, SAHAI A, & GOSWAMI, N. 2015. Effect of nitrogen doping on structural and optical properties of ZnO nanoparticles. *Progress in Natural Science: Mater. Inter.*, 25(4), 300-309.
- OKPARA ENYIOMAC, OMOLOLA EFAYEMI, EL-SAYED MSHERIF, HARRI JUNAEDI & ENO EEBENSO. 2020. Green wastes mediated zinc oxide nanoparticles: synthesis, characterization and electrochemical studies." *Mater.* 13, 19: 4241.

- MANZOOR U, SIDDIQUE S, AHMED R, NOREEN Z, BOKHARI H, & AHMAD I. 2016. Antibacterial, structural and optical characterization of mechano-chemically prepared ZnO nanoparticles. *PLoS One*, 11(5), e0154704.
- YANG BUJUN, M ZANG, M WU, H ZANG. 2019. SYNTHESIS of biochar-based Cu₂O nanoparticles and their antibacterial activity against *Escherichia coli*. *Inorg. Nano-Met. Chem.* 49(1):12-16.
- ELERYAN A, HASSAAN MA, AIGBE UO, UKHUREBOR KE, ONYANCHA RB, EL-NEMR M. A, & EL NEMR A. 2023. Kinetic and isotherm studies of Acid Orange 7 dye absorption using sulphonated mandarin biochar treated with TETA. *Biomass Convers. Biorefin*, 1-12.
- HOSEINZADEH ABOLGHASEM, AZIZ HABIBIYANGJEH, & MAHDI DAVARI .2016. Antifungal activity of magnetically separable Fe₃O₄/ZnO/AgBr nanocomposites prepared by a facile microwave-assisted method. *Prog. Nat. Sci. Mater. Int.* 26(4):334-340.
- ZHANG LIN-JIONG. 2014. Synthesis and antifungal activity of 1, 3, 4-thiadiazole derivatives containing pyridine group. *Lett. Drug Des. Discov.* 11(9):1107-1111.
- NGUYEN VAN THANG. 2019. Antibacterial activity of TiO₂-and ZnO-decorated with silver nanoparticles. *J. Compos. Sci.* 3(2):61.
- JAIN M. 2018. Development of iron oxide/activated carbon nanoparticle composite for the removal of Cr (VI), Cu (II) and Cd (II) ions from aqueous solution. *Water Resour. & Indus*, 20: p. 54-74.
- AMEH P. 2023. Synthesized iron oxide nanoparticles from *Acacia nilotica* leaves for the sequestration of some heavy metal ions in aqueous solutions. *J. Chem. Lett.*, 4(1): p. 38-51.
- DUBEY RK, TRIPATHI V, DUBEY PK, SINGH HB, & ABHILASH PC. 2016. Exploring Rhizospheric interactions for agricultural sustainability: the need of integrative research on multi Trophic interactions. *J. Clean. Prod.*, 115, 362-365.
- HO YS, & G MCKAY. 1998. A comparison of chemisorption kinetic models applied to pollutant removal on various sorbents. *Process Saf. Environ. Prot.* 76(4), p. 332-344.
- KAEWSARN P. 2002. Biosorption of copper (II) from aqueous solutions by pre-treated biomass of marine Algae *Padina sp.* *Chemosph*, 47(10), p. 1081-1085.
- CHANANI J, BUAZAR F, & NIKPOUR Y. 2023. Promoted photocatalytic activity of green titanium oxide-clay nanocomposite toward polychlorinated biphenyl degradation in actual samples. *Water, Air, & Soil Poll.*, 234(6), 364.